

	<h1>REOSAN OPACO</h1>	<p style="text-align: center;"><b>SPECIFICATIONS</b></p>   <p style="text-align: center;">Rev. 0 – Ed. 1</p>
---	---------------------------	---

### SPECIFICATIONS AND FIELDS OF EMPLOYMENT

REOSAN OPACO is a wall cleaning water-based paint presenting a high wide-ranging power. It is used to paint mould-contaminated walls and contains a potent fungicide able to remove completely any type of mould, alga, fungus etc..

Besides having a restoring effect, REOSAN OPACO prevents the forming of the above mentioned moulds on new walls.

It has a high covering power and an excellent flaking and washing resistance which guarantee a pleasant mat effect; that is why it is employed in those surroundings, like hospitals, schools, communities, cheese factories, bathrooms, kitchens, etc., where a perfect cleanliness is required.

The restoring cycle of the REOSAN LINE is guaranteed, by a written certification, for three years as from the application date.

### COMPOSITION

REOSAN is a synthetic copolymer-based product in emulsion, wide-ranging anti-mould, containing titanium dioxide, special reinforcing fillers and additives. It does not contain any noxious substance such as lead and chrome-based solvents and pigments.

### METHODS OF APPLICATION

#### New walls

Sand, clean out and apply a coat of FISSATIVO REOSAN diluted in water from a ratio of 1 to 5 to a ratio of 1 to 10, depending on the support absorption degree.

Let it dry for at least 4 hours and apply two coats of water paint REOSAN, opportunely diluted, (see technical data) at a distance of 4/5 hours after the application of the first coat.

#### Moulded walls

Apply evenly the DETERGENTE REOSAN ( diluted in water in the ratio of 1 to 10) on the moulded parts; 4-5 hours after, when the detergent is completely dry, clean strongly the blackened parts using a suitable brush and/or sandpaper. Apply a coat of FISSATIVO REOSAN diluted in water from a ratio of 1 to 5 to a ratio of 1 to 10 depending on the absorption degree of the support.

Let it dry for at least 4 hours and apply two coats of water paint REOSAN ANTICONDENSA, opportunely diluted, (see technical data) at a distance of 4/5 hours after the application of the first coat.

### TECHNICAL DATA

SPECIFIC WEIGHT:	1.410 +/- 50 grams/litres
FILM ASPECT:	MAT
COLOURS:	white (other colours by request)
VISCOSITY:	thixotropic aspect
YIELD:	8 / 10 m <sup>2</sup> /litres (for two coats)
DILUTION:	10-20% in water for brush and roller application 30% in water for spray application
PACKAGE:	13-litres tin-plated cases available 5 / 2,5-litres polyethylene cases available
DRYING:	to the touch: 30 minutes; completely: 24 hours at 20°C
APPLICATION:	paintbrush, roller, spray
PRESERVATION:	36 months in the intact packages, away from temperature changes

### ITEM OF SPECIFICATIONS

Painting of indoor walls through mat anti-mould water-based paints like the REOSAN OPACO, produced by SPIVER Ltd., applied in two paintbrush or roller coats with an average consumption of 0.125 litres/m<sup>2</sup>, prior sterilizing treatment with the DETERGENTE REOSAN, produced by SPIVER Ltd., diluted in water in the ratio of 1 to 10 and prior setting treatment using the FISSATIVO REOSAN, produced by SPIVER Ltd., diluted in water from a ratio of 1 to 5 to a ratio of 1 to 10 depending on the absorption degree of the support.

Price inclusive of the material and implementation, except the scaffoldings per square metre: £.....

NB The above-mentioned data are susceptible of variations. Spiver Ltd. is not responsible for any negative result depending on the application of the product out of the Company's control and on the agents unrelated to the product quality.